



Asahiklin AK225

Light Duty Degreaser 1663

Introduction

AK225 Neat is 100% HCFC-225. Completely non-flammable, safe on metals and plastics, the straight AK225 is an excellent solvent for metal degreasing. AK225 offers superior cleaning for LOX applications, video heads, reflector glasses for laser printers, scanners and other equipment that requires optimal cleanliness.

Features / Benefits Non-Flammable Rapidly Evaporating Safe on Most Plastics Zero Residue

Physical Properties	
Boiling Point	54°C / 129°F
Flash Point (TCC)	None
Evaporation Rate	>1
Surface Tension	
Kauri-Butanol (KB Value)	

Chemical Components

3,3-Dichloro-1,1,1,2,2-	32-42%-Aerosol
pentafluoropropane (HCFC-225ca) (422-56-0)	40-50%-Bulk
1,3-Dichloro-1,1,2,2,3-	40-50%-Aerosol
pentafluoropropane (HCFC-225cb) (507-55-1)	50-60%-Bulk
Aerosol - 1,1,1,2-Tetrafluoroethane(811-97-2)	18-23%
Carbon Dioxide (Aerosol Propellant)(124-38-9)	1-2%

Environmental Policy

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Packaging and Availability

Asahiklin AK225 may be ordered in the following container sizes:

1663-8S	8 Ounce Aerosol
1663-18S	18 Ounce Aerosol
1663-G	1 Gallon in Glass
1663-5G	55 Pounds in Metal
1663-54G	660 Pounds in Metal

Techspray® products are supported by a global sales, technical and customer services resources.

For additional technical information on this product or other Techspray® products in the United States, call the technical sales department at 800-858-4043, email tsales@techspray.com or visit our web site at: www.techspray.com.

North America Tech Spray L.P. P.O. Box 949 Amarillo, TX 79105 800-858-4043 email: tsales@techspray.com Europe ITW Contamination Control Skejby Nordlandsvej 307 DK-8200 Aarhus N +45 87 400 220 email: info@itw-cc.com Countries Outside US Call to locate a distributor in your country.

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray® be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory.



Tech Spray, L.P. P.O. Box 949 Amarillo, TX 79105 www.techspray.com Aerosol MSDS English French German Italian Spanish

Bulk MSDS
English
French
German
Italian
Spanish



